

CLASS C SMOOTH FRP WALL PANELS

Part Number/Identifier: FSQ

6547
rev. 1
July 2004

Product:

Structoglas Class C (FSQ) fiberglass reinforced flat panels will not rot, rust, corrode, stain, dent, peel, or splinter. Panels exhibit a high strength-to-weight ratio with expansion/contraction values similar to aluminum.

Purpose:

Structoglas panels are recommended for use on interior walls requiring a Class C fire-rated finish for agricultural, commercial and industrial buildings where sanitation, durability, aesthetics and safety are critical.

TABLE ONE: PHYSICAL PROPERTIES

Typical Values		Test Method
Property	FSQ 0.09" (2.3 mm)	
Tensile Strength	6,000 psi (41 MPa)	ASTM D790
Tensile Modulus	550,000 psi (3792 MPa)	ASTM D790
Flexural Strength	9,000 psi (62 MPa)	ASTM D638
Flexural Modulus	500,000 psi (3447 MPa)	ASTM D638
IZOD Impact Strength	3.5 ft•lbs/in (0.19 J/mm)	ASTM D256
Barcol Hardness	25-35	ASTM D2583
Coefficient of Linear Thermal Expansion	2.25×10^{-5} in/in•°F ($41 \mu\text{m}/\text{m}\cdot\text{°C}$)	ASTM D696
Water Absorption	<0.75% in 24 hrs @77°F (25°C)	ASTM D570

TABLE TWO: DESIGN TABLE

Product Code	Nominal Thickness	Colors	Size	Finish
FSQ	0.09" (2.3 mm)	1130 White	4' x 8' (1.2 m x 2.4 m) 4' x 9' (1.2 m x 2.7 m) 4' x 10' (1.2 m x 3.0 m) 4' x 12' (1.2 m x 3.7 m)	Smooth

SPECIFICATIONS:

These panels are manufactured by a continuous laminating process in lengths as required.

Composition:

1. Reinforcement: random chopped fiberglass roving.
2. Resin mix: modified polyester copolymer and inorganic fillers and pigments.

Finished Panel Quality:

1. Panels shall have a wear side with a pebble-like embossed or smooth finish. Color shall be uniform throughout, as specified. The backside shall be smooth. Backside imperfections which do not affect functional properties are not cause for rejection.
2. Physical properties shall be as set forth in Table 1.
3. Product quality standards and tolerances for panel weight and thickness shall be as set forth in Kemlite Company's is Quality Control Procedures/Standards which are available on request.
4. Dimensions shall be as specified on purchase order, subject to the following tolerances:
Width: $\pm 1/8"$ (3.2 mm)
Length: $\pm 1/8"$ (3.2 mm) up to 12' (3.7 m)
Squareness: not more than $1/8"$ (3.2 mm) out of square
5. Panels shall be installed in accordance with manufacturer's guidelines as set forth in the Structoglas "Installation Guide."

FABRICATING RECOMMENDATIONS:

Note: Protect your eyes with goggles and cover your nose and mouth with a filter mask when cutting Structoglas panels.

Hand fabrication: Drilling-high speed drill bit (60° cutting angle, with 12°-15° clearance) or hole saw.

Cutting: Sheet metal shears or circular saw with reinforced carborundum or carbide-tipped blade.

Production fabrication: Use carbide-tipped tools. Straight cuts can be sheared (90° cutting edge with 0.002" (0.05 mm) clearance) or sawed. For irregular cuts, use die punch or band saw.

STORAGE:

All Structoglas products should be stored indoors.

SERVICEABLE TEMPERATURE RANGE:

Panels will perform in temperatures from -40°F (-40°C) to 150°F (66°C). For use in environments beyond this range contact Kemlite Company for recommendations.

LIMITATIONS:

Near heat source - Structoglas panel products may discolor when installed behind or near any heat source which radiates temperatures exceeding 130°F (55°C), such as cookers, ovens, and deep fryers. Not intended for exterior use.

NOTICE:

Panels will provide a clean, aesthetically-pleasing finished installation. However, by nature, fiberglass reinforced plastic paneling may occasionally have small areas that are aesthetically unacceptable for use. Panels should be inspected on-site prior to installation. If any portion of material does not provide an acceptable appearance, Kemlite Company should be notified at once. Upon verification of unacceptability, that portion of material will be replaced by Kemlite Company. Kemlite Company's sole responsibility is for the replacement of defective materials but not for labor or other handling or installation expenses.

CERTIFICATION:

- A. Flame spread 200 or less, smoke developed 450 or less (per ASTM E-84)
- B. Meets USDA/FSIS requirements
- C. Frp does not support mold or mildew (per ASTM D3273 and ASTM D3274)

We believe all information given is accurate. It is offered in good faith, but without guarantee. Since conditions of use are beyond our control, all risks are assumed by the user. Nothing herein shall be construed as a recommendation for uses which infringe on valid patents or as extending a license under valid patents.

FLAME SPREAD AND SMOKE DEVELOPMENT RATINGS

The numerical flame spread and smoke development ratings are not intended to reflect hazards presented by Kemlite Company products or any other material under actual fire conditions. These ratings are determined by small-scale tests conducted by Underwriters Laboratories and other independent testing facilities using the American Society for Testing and Materials E-84 test standard (commonly referred to as the "Tunnel Test"). KEMLITE COMPANY PROVIDES THESE RATINGS FOR MATERIAL COMPARISON PURPOSES ONLY. Like other organic building materials (e.g. wood), panels made of fiberglass reinforced plastic resins will burn. When ignited, frp may produce dense smoke very rapidly. All smoke is toxic. Fire safety requires proper design of facilities and fire suppression systems, as well as precautions during construction and occupancy. Local codes, insurance requirements and any special needs of the product user will determine the correct fire-rated interior finish and fire suppression system necessary for a specific installation.



CRANE Kemlite®

A Crane Co. Company

Form 6547 Rev. 01 (997)